

Technical data sheet Superwand DS insulation panel

Product features

Application:	The SUPERWAND DS is used for internal insulation of exterior walls The SUPERWAND DS can easily be processed and glued full-face on the wall using dispersion adhesive. The SUPERWAND DS can be papered or tiled with the conventional products after smoothing and filling joints. Through the white surface, it is also particularly suitable for thin wallpaper and renovating mat.		
Description:	Sandwich element with PUR - rigid foam core, cardboard layer on both sides (from cellulose pulp cardboard, polyethylene (PE), aluminium foil, tissue paper)		
Formats:	1'250 x 800 x 10 mm, 1'250 x 800 x 20 mm		
Behaviour to external influences:	Panel	With approval for building products	
	Foam	no water absorption, only in cut cells	
	Cover layer	Multilayer with aluminium foil	
Chemical behaviour:	Foam	chemically inert, resistant to almost all solvents and adhesives	
	Cover layer	resistant to humidity and commercially customary paints and adhesives	
Thermal conductivity:	Measured thermal conductivity = 0,025 W/mK Theoretical value after aging = 0,036 W/mK		
Vapour diffusion resistance:	$S_D = 550$ m equiv. air space thickness		
Temperature resistant:	permanent	$T_p = -20$ to 100 °C	
	short-time	$T_s =$ up to 160 °C	
Compliance with the following standards:	DIN EN 13 165 (from January 2004) DIN 4102 B2, DIN EN 13 501-1(from January 2004) DIN EN ISO 9001 1994-08		

Technical values and tolerances

			Tolerance
Thickness:	10,0 mm	20,0 mm	$\pm 0,6$ mm
Volume weight:	45,0 kg/m ³	45,0 kg/m ³	± 5 kg/m ³
Basis weight: (approx. values)	1'070 g/m ²	1'475 g/m ²	-
Fire performance:	B2	B2	
Measured U-value:	2,50 W/m ² K	1,25 W/m ² K	
Compression resistance at 10 % copression set:	0,38 N/mm ²	0,42 N/mm ²	$\pm 0,03$ N/mm ²
Reset at 10% compression set:	~ 95 %	~ 95 %	-

All data are based on our knowledge and experience. It's intended as an advice without legally binding.

August 31th 2016